

## Italiano Carta Patinata Matt

Proprietà			Unità	Tolleranza	115	130	150	170
Grammatura	ISO 536	TAPPI T410	g/m <sup>2</sup>	± 4%	115	130	150	170
Spessore	ISO 534	TAPPI T411	µm	± 4%	115	130	150	170
Volume	ISO 534	TAPPI T411	cm <sup>3</sup> /g	-	1,00	1,00	1,00	1,00
Umidità relativa		TAPPI T502	%	± 7	50	50	50	50
Opacità	ISO 2471	TAPPI T519	%	-2	95,0	96,0	97,0	98,0
Lucido	ISO 8254-1	TAPPI T480	%	± 5	10	10	10	10
Rugosità PPS	ISO 8791-1	TAPPI T555	µm	± 1	4,0	4,0	4,0	4,0
Bianco CIE D65	ISO 11475			± 3	119	119	119	119

- Ultima revisione: **23-09-14**
- I valori sono soggetti a modifiche senza preavviso.



## English Coated Paper 2 Sides Matt

Property			Units	Tolerance	115	130	150	170
Substance	ISO 536	TAPPI T410	g/m <sup>2</sup>	± 4%	115	130	150	170
Thickness	ISO 534	TAPPI T411	µm	± 4%	115	130	150	170
Bulk	ISO 534	TAPPI T411	cm <sup>3</sup> /g	-	1,00	1,00	1,00	1,00
Relative Humidity		TAPPI T502	%	± 7	50	50	50	50
Opacity	ISO 2471	TAPPI T519	%	-2	95,0	96,0	97,0	98,0
Paper Gloss	ISO 8254-1	TAPPI T480	%	± 5	10	10	10	10
Roughness PPS	ISO 8791-1	TAPPI T555	µm	± 1	4,0	4,0	4,0	4,0
Whiteness CIE	ISO 11475			± 3	119	119	119	119

- Last updating: **23-09-14**
- Values are subject to change without notice.



## Español Estucado 2 Caras Mate

Propiedad			Unidades	Tolerancia	115	130	150	170
Gramaje	ISO 536	TAPPI T410	g/m <sup>2</sup>	± 4%	115	130	150	170
Calibre	ISO 534	TAPPI T411	µm	± 4%	115	130	150	170
Volumen Especifico	ISO 534	TAPPI T411	cm <sup>3</sup> /g	-	1,00	1,00	1,00	1,00
Humedad relativa		TAPPI T502	%	± 7	50	50	50	50
Opacidad	ISO 2471	TAPPI T519	%	-2	95,0	96,0	97,0	98,0
Brillo de papel	ISO 8254-1	TAPPI T480	%	± 5	10	10	10	10
Rugosidad PPS	ISO 8791-1	TAPPI T555	µm	± 1	4,0	4,0	4,0	4,0
Blancura CIE	ISO 11475			± 3	119	119	119	119

- Última actualización: **23-09-14**
- Los valores están sujetos a cambio sin aviso previo.



## Français Couché 2 Faces Mat

Propiedad			Unités	Tolérance	115	130	150	170
Grammage	ISO 536	TAPPI T410	g/m <sup>2</sup>	± 4%	115	130	150	170
Épaisseur	ISO 534	TAPPI T411	µm	± 4%	115	130	150	170
Main	ISO 534	TAPPI T411	cm <sup>3</sup> /g	-	1,00	1,00	1,00	1,00
Humidité relative		TAPPI T502	%	± 7	50	50	50	50
Opacité	ISO 2471	TAPPI T519	%	-2	95,0	96,0	97,0	98,0
Brillance du papier	ISO 8254-1	TAPPI T480	%	± 5	10	10	10	10
Rugosité PPS	ISO 8791-1	TAPPI T555	µm	± 1	4,0	4,0	4,0	4,0
Blancheur CIE	ISO 11475			± 3	119	119	119	119

- Dernière actualisation: **23-09-14**
- Ces valeurs sont sujettes à modification sans avis préalable



## Deutsch 2-seitig Gestrichen Matt

Kennzeichen			Massenheit	Toleranz	115	130	150	170
Grammatur	ISO 536	TAPPI T410	g/m <sup>2</sup>	± 4%	115	130	150	170
Dicke	ISO 534	TAPPI T411	µm	± 4%	115	130	150	170
Volumen	ISO 534	TAPPI T411	cm <sup>3</sup> /g	-	1,00	1,00	1,00	1,00
Relative Feuchtigkeit		TAPPI T502	%	± 7	50	50	50	50
Opazität	ISO 2471	TAPPI T519	%	-2	95,0	96,0	97,0	98,0
Papier Glanz	ISO 8254-1	TAPPI T480	%	± 5	10	10	10	10
PPS	ISO 8791-1	TAPPI T555	µm	± 1	4,0	4,0	4,0	4,0
Weisse CIE D65	ISO 11475			± 3	119	119	119	119

- Letzte Änderung: **23-09-14**
- Diese Werte können ohne vorherige Ankündigung geändert werden

