



## Especificaciones Técnicas Technical Specification

Calidad / Tipo / Grade / Qualité / Typ

# 730 Cartulina Ibiza

CARTULINA ESTUCADA REVERSO BLANCO  
CARTONCINO PATINATO EXTRAFINE, RETRO BIANCO INTERNO BIANCHITO  
FULLY COATED BLEACHED BOARD  
CARTON BLANC COUCHE SUR VERSO BLANC, INTERIEUR BLANCHI  
VOLLGESTRICHENER CHROMOCARTON – SBS

Gramaje Substance	Espesor Caliper	Ind. de Mano Bulk	Rigidez Taber (15°) Stiffness Taber		Rigidez DIN (7,5°) Stiffness DIN	
			Sm. Md	St. Cd	Sm. Md	St. Cd
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m2	mm	cm3/g	mN.m	mN.m	N.mm	N.mm
250	0,280	1,12	5,8	2,7	10,9	5,1
275	0,315	1,15	7,9	3,3	14,9	6,2
300	0,345	1,15	10,6	4,3	19,9	8,1
325	0,380	1,17	14,0	5,5	26,3	10,3
350	0,410	1,17	17,9	6,9	33,7	13,0
375	0,445	1,19	21,3	8,6	40,1	16,2
450	0,545	1,21	38,6	14,8	72,1	27,8
500	0,610	1,22	52,3	19,6	98,4	36,9

### Blancura Xenon ISO 2470 Xenon Brightness ISO 2470

<b>Cara / Top</b>	87,5 % +/- 2
<b>Reverso / Back</b>	91 % +/- 2

### Tolerancias – Muestreo ISO 186 Tolerances – Sampling ISO 186

<b>Gramaje / Substance</b>	+/- 3 % Sobre la media del pedido On the average of the order
<b>Espesor / Caliper</b>	+/- 6 % Sobre muestras individuales (95% de los valores) For single determinations (95% of values)
<b>Ind. de mano / Bulk</b>	+/- 5 % Sobre muestras individuales (95% de los valores) For single determinations (95% of values)
<b>Rigidez / Stiffness -</b>	-15 % Sobre muestras individuales (95% de los valores) For single determinations (95% of values)
<b>Cond. ambientales / Test conditions</b>	<b>T: 23 +/- 1° C      RH: 50 +/- 2%</b>

03 - 2016

Head Office:  
SARRIO PAPELERA DE ALMAZAN, S.L.U.  
c/ Selva 2, Edificio Planta 3ª (Polígono Mas Blau)  
08820 El Prat de Llobregat  
Tel. +34 93475-91-00 Fax +34 93478-06-73  
Empresa Certificada ISO 9001