

grupo Portucel Soporcel



SOPORSET
PREMIUM OFFSET

PREMIUM OFFSET FOLIO + REELS

Technical References – Targets only, without tolerances mentioned

	Whiteness	Opacity	Moisture	Bendtsen Roughness	Thickness	Bulk
	CIE	% (minimum)	%	ml/min	µm	µm/g/m ²
	ISO 11475	ISO 2471	ISO 287	ISO 8791/2	ISO 534	—
60g/m²	161	87,0	6,2	150	80	1,33
70 g/m²	161	91,0	6,2	150	92	1,31
80 g/m²	161	94,0	6,0	150	106	1,33
90 g/m²	161	95,0	6,0	150	116	1,29
100 g/m²	161	96,0	5,8	150	128	1,28
110 g/m	161	97,0	5,8	150	141	1,28
120 g/m	161	98,0	5,8	150	150	1,25

Additional Information about grupo Portucel Soporcel Mills and Products:

Grupo Portucel Soporcel mills are chain-of-custody certified by the Smartwood Program of the Rainforest Alliance in accordance with FSC-40-004 and FSC-40-005 (SW-COC/CW 001829).

In accordance with the requirements of ISO 9706 standard

Elemental Chlorine Free (ECF)

Quality Standard ISO 9001

Environmental Standard ISO 14001

Occupational Health and Safety Standard OHSAS 18001

HP/Indigo certification for uncoated papers in the last generation of machines with SPP system (HP/Indigo 5500 and 7000/7500). Good papers suitable for less demanding applications and ink coverages, making them ideal for black & white applications. HP/Indigo media locator in the internet: www.hp.com/go/medialocator

grupo Portucel Soporcel



SOPORSET
PREMIUM OFFSET

PREMIUM OFFSET FOLIO

Technical References – Targets only, without tolerances mentioned

	Whiteness CIE	Opacity % (minimum)	Moisture %	Bendtsen Roughness ml/min	Thickness µm	Bulk µm/g/m ²
	ISO 11475	ISO 2471	ISO 287	ISO 8791/2	ISO 534	—
135 g/m²	161	95,0	6,0	150	155	1,15
150 g/m²	161	97,0	6,0	150	172	1,15
170 g/m²	161	98,0	6,0	200	205	1,21
190 g/m²	161	98,0	6,0	200	230	1,21
225 g/m²	161	98,0	6,0	200	275	1,22
250 g/m²	161	98,0	6,0	200	305	1,22
300 g/m²	161	98,0	6,0	200	365	1,22
350 g/m²	161	98,0	6,0	200	425	1,21

Additional Information about grupo Portucel Soporcel Mills and Products:

Grupo Portucel Soporcel mills are chain-of-custody certified by the Smartwood Program of the Rainforest Alliance in accordance with FSC-40-004 and FSC-40-005 (SW-COC/CW 001829).

In accordance with the requirements of ISO 9706 standard

Elemental Chlorine Free (ECF)

Quality Standard ISO 9001

Environmental Standard ISO 14001

Occupational Health and Safety Standard OHSAS 18001