



Especificaciones Técnicas Technical Specification

Calidad / Tipo / Grade / Qualité / Typ

713 Escudo Madera

CARTON ESTUCADO REVERSO MADERA
 CARTONCINO PATINATO EXTRAFINE CON RETRO MANILLA
 FULLY COATED WHITE LINED CHIPBOARD WITH MANILLA BACK
 CARTON BLANC COUCHE SUR VERSO BOIS, INTERIEUR GRIS
 VOLLGESTRICHENER CHROMOTRIplexKARTON – GT

Gramaje Substance	Espesor Caliper	Ind. de Mano Bulk	Rigidez Taber (15°) Stiffness Taber		Rigidez DIN (7,5°) Stiffness DIN	
			Sm. Md	St. Cd	Sm. Md	St. Cd
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m2	mm	cm3/g	mN.m	mN.m	N.mm	N.mm
250	0,315	1,26	6,5	2,9	12,2	5,5
275	0,355	1,29	8,6	3,7	16,2	7,0
300	0,385	1,28	11,3	4,8	21,3	9,0
325	0,425	1,31	14,5	6,1	27,3	11,5
350	0,450	1,30	18,0	7,3	33,9	13,7
375	0,495	1,32	23,0	9,3	43,2	17,5
400	0,530	1,33	28,3	11,3	53,2	21,3
450	0,605	1,34	38,9	15,1	73,2	28,4
500	0,675	1,35	53,0	20,1	99,7	37,8

Blancura Xenon ISO 2470 Xenon Brightness ISO 2470

Cara / Top 87,5% +/- 2

Reverso /Back 50 % +/- 2

Tolerancias – Muestreo ISO 186 Tolerances – Sampling ISO 186

Gramaje / Substance +/- 3 % Sobre la media del pedido
On the average of the order

Espesor / Caliper +/- 6 % Sobre muestras individuales (95% de los valores)
For single determinations (95% of values)

Ind. de mano / Bulk +/- 5 % Sobre muestras individuales (95% de los valores)
For single determinations (95% of values)

Rigidez / Stiffness - -15 % Sobre muestras individuales (95% de los valores)
For single determinations (95% of values)

Cond. ambientales / Test conditions T: 23 +/- 1° C RH: 50 +/- 2%

01 - 2016

Head Office:
 RenoDeMedici S.p.A.
 Via Durini, 18 – 20122 Milano (MI) – Italy
 Tel. +39 02752881 r.a. – Fax +39 0275288642
 www.renodemedici.it
 Azienda certificata ISO 9001

Spain:
 RenoDeMedici Iberica S.L.Unipersonal
 C/Selva 2 , Edificio planta 3ª 1º Polígono Mas Blau – 08820 El
 Prat de Llobregat
 Barcelona
 Tel. +34 93 4759100 – Fax +34 93 4780673
 Empresa certificada ISO 9001