

grupo Portucel Soporcel



Technical References – Targets only, without tolerances mentioned

	Whiteness CIE	Opacity %	Moisture %	Bendtsen Roughness ml/min	Thickness μm	Bulk $\mu\text{m/g/m}^2$
	ISO 11475	ISO 2471	ISO 287	ISO 8791/2	ISO 534	—
80 g/m²	171	94,5	4,8	160	106	1,33
90 g/m²	171	95,5	4,8	140	116	1,29
100 g/m²	171	96,0	4,5	140	123	1,23
110 g/m²	171	97,0	4,5	120	134	1,22

Additional Information about grupo Portucel Soporcel Mills and Products:

Grupo Portucel Soporcel mills are chain-of-custody certified by the Smartwood Program of the Rainforest Alliance in accordance with FSC-40-004 and FSC-40-005 (SW-COC/CW 001829).

In accordance with the requirements of ISO 9706 standard

Elemental Chlorine Free (ECF)

Quality Standard ISO 9001

Environmental Standard ISO 14001

Occupational Health and Safety Standard OHSAS 18001

HP/Indigo certification for uncoated papers in the last generation of machines with SPP system (HP/Indigo 5500 and 7000/7500).

Good papers suitable for less demanding applications and ink coverages, making them ideal for black & white applications.

HP/Indigo media locator in the internet: www.hp.com/go/medialocator

grupo Portucel Soporcel



Technical References – Targets only, without tolerances mentioned

	Whiteness CIE	Opacity % (minimum)	Moisture %	Bendtsen Roughness ml/min	Thickness µm	Bulk µm/g/m ²
	ISO 11475	ISO 2471	ISO 287	ISO 8791/2	ISO 534	—
135 g/m²	171	96,5	5,4	150	155	1,15
160 g/m²	171	97,5	5,4	150	190	1,19

Additional Information about grupo Portucel Soporcel Mills and Products:

Grupo Portucel Soporcel mills are chain-of-custody certified by the Smartwood Program of the Rainforest Alliance in accordance with FSC-40-004 and FSC-40-005 (SW-COC/CW 001829).

In accordance with the requirements of ISO 9706 standard

Elemental Chlorine Free (ECF)

Quality Standard ISO 9001

Environmental Standard ISO 14001

Occupational Health and Safety Standard OHSAS 18001