

# PRO-DESIGN SPECIFICATIONS

## PRODUCT RANGE

	90 G/M <sup>2</sup>	100 G/M <sup>2</sup>	120 G/M <sup>2</sup>	160 G/M <sup>2</sup>	200 G/M <sup>2</sup>	250 G/M <sup>2</sup>	300 G/M <sup>2</sup>	350 G/M <sup>2</sup>
	500x	500x	250x	250x	250x	125x	125x	100x
A4	●	●	●	●	●	●	●	○
A3	●	●	●	●	●	●	●	○
SRA3	●	●	●	●	●	●	●	●
SRA2	●	●	● 500x	●	●	● 250x	● 500x	○

## SHEETS

## REELS

500 mm; 1200/76 mm	●	●	●	●	●	●	●	●
<b>XEIKON</b> 500 mm; 480/152 mm	●	●	●	●	●	●	●	●
450 mm; 480/152mm								

## TECHNICAL SPECIFICATIONS

	90 G/M <sup>2</sup>	100 G/M <sup>2</sup>	120 G/M <sup>2</sup>	160 G/M <sup>2</sup>	200 G/M <sup>2</sup>	250 G/M <sup>2</sup>	300 G/M <sup>2</sup>	350 G/M <sup>2</sup>
CIE Whiteness (ISO 11475)	168	168	168	168	168	168	168	168
Opacity % (ISO 2471)	min 92	min 95	min 95	min 96	min 98	min 98	min 99	min 99
Thickness μm (ISO 534)	98	109	125	158	196	250	300	350
Smoothness Bekk (sec) (ISO 5627)	130	140	140	140	135	100	75	75
Formation (Kajaani Index)	110	110	110	110	110	110	110	110
Stiffness MD/CD (ISO 2493)	125/65	165/85	225/145	455/260	700/400	1060/640	1500/940	2150/1300

## CERTIFICATIONS

