



J. VILASEGA S. A.

FABRICA DE PAPEL DESDE 1.714

REGISTRO AHUESADO

| Specification | Unit | Norm | Value | Tolerances |
|---|-------------|-------------|--|-------------------|
| Gramaje Substance Grammage | g/m^2 | ISO 536 | 90, 100, 112, 140, 160 | +/- 4 % |
| Espesor Thickness Épaisseur | μm | ISO 534 | 90 gr. 105 100 gr. 115 112 gr. 123 140 gr. 154 160 gr. 168 | +/- 5 % |
| Porosidad Porosity Porosité | Índice | ISO 5636-5 | > 15 | |
| Lisura Bekk Smoothness Bekk Lissé Bekk | s | ISO 5627 | 50 | +/- 10 |
| Humedad absoluta Absolute moisture Humidité absolute | % | ISO 287 | 7 | +/- 1 |

Los datos citados son indicativos. La estructura y los valores de la información de los productos pueden ser modificados.

The figures are indicative. The structure and values of the product information can be modified.

Les chiffres cités sont à titre indicatif. La structure et les valeurs de l'information sur le produit peuvent être modifiées



Ref: 805/007/02/R1

Marzo 2023