



**J.VILASEGA S. A.**

FABRICA DE PAPEL DESDE 1.714

## **CARTULINA POSAVASOS**

<b>Specification</b>	<b>Unit</b>	<b>Norm</b>	<b>Value</b>	<b>Tolerance</b>
<b>Gramaje</b> <b>Substance</b> <b>Grammage</b>	$g/m^2$	<b>ISO 536</b>	230 gr 350 gr	+/- 10 +/- 12
<b>Espesor</b> <b>Caliper</b> <b>Épaisseur</b>	$\mu m$	<b>ISO 534</b>	230 gr 326 350 gr 497	+/- 12 +/- 24
<b>Porosidad</b> <b>Porosity</b> <b>Porosité</b>	<b>Índice</b>	<b>ISO 5636-5</b>	5	+/- 2
<b>Lisura Bekk</b> <b>Smoothness Bekk</b> <b>Lissé Bekk</b>	s	<b>UNE 57093</b>	7	+/- 4
<b>Humedad absoluta</b> <b>Absolute moisture</b> <b>Humidité absolue</b>	%	<b>ISO 287</b>	7	+/- 0,5
<b>Blancura</b> <b>Whiteness</b> <b>Blancheur</b>	<b>CIE</b> <b>C,10°</b>	<b>ISO 11475</b>	155	+/- 3

100 % Pasta química  
Papel sin encolar

Los datos citados son indicativos.  
La estructura y los valores de la información de los productos pueden ser modificados.



Ref: 802/110/00/R6  
Enero 2021