

Technical Data Sheet

MULTICOPY ZERO 80GR

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m ²	80
Thickness	ISO 534	µm	105
Bulk	ISO 534		1.31
Moisture Content	ISO 287	%	4.1
Roughness	ISO 8791	Bendtsen ml/min	160
Whiteness	ISO 11475	CIE	168
Brightness D65	ISO 2470-2	%	114
Opacity	ISO 2471	%	92

Production sites:

The production mills operate in compliance with the following standards



Special Attributes:



References:
Product is made taking into account requirements of DIN EN 12281
ISO 45001 - Health & Safety
Product made from TCF Pulp
ISO 50001 - Energy