

EN Coated Paper 2 Sides Silk

Property			Unit	Tolerance					
Substance	ISO 536	TAPPI T410	gsm	± 4%	135	150	200	250	300
Thickness	ISO 534	TAPPI T411	µm	± 4%	115	131	166	220	265
Brightness R457 D65	ISO 2470-2	-	%	± 2	95	95	95	95	95
Whiteness CIE D65/10°	ISO 11475	-	-	± 3	119	119	119	119	119
Opacity	ISO 2471	TAPPI T519	%	-2.0	96	97			
Roughness Parker	ISO 8791-4	TAPPI T555	µm	±30%	1,8	1,8			
Relative Humidity	-	TAPPI T502	%	± 7	50	50	50	50	50

- Last updated: **27-10-17**
- Values are subject to change without notice.

ES Estucado 2 Caras Semimate

Propiedad			Unidades	Tolerancia					
Gramaje	ISO 536	TAPPI T410	gsm	± 4%	135	150	200	250	300
Calibre	ISO 534	TAPPI T411	µm	± 4%	115	131	166	220	265
Brightness R457 D65	ISO 2470-2	-	%	± 2	95	96	96	96	96
Blancura CIE D65/10°	ISO 11475	-	-	± 3	119	119	119	119	119
Opacidad	ISO 2471	TAPPI T519	%	-2.0	96	97,0	0	0	0
Rugosidad Parker	ISO 8791-4	TAPPI T555	µm	±30%	2	1,8	0	0	0
Humedad relativa	-	TAPPI T502	%	± 7	50	50	50	50	50

- Última actualización: **27-10-17**
- Los valores están sujetos a cambio sin aviso previo.

FR Couché 2 Faces Demi-mat

Propriété			Unité	Tolérance					
Grammage	ISO 536	TAPPI T410	gsm	± 4%	135	150	200	250	300
Épaisseur	ISO 534	TAPPI T411	µm	± 4%	115	131	166	220	265
Blancheur R457 D65	ISO 2470-2	-	%	± 2	96	96	96	96	96
Blancheur CIE D65/10°	ISO 11475	-	-	± 3	119	119	119	119	119
Opacité	ISO 2471	TAPPI T519	%	-2.0	96,0	97,0	0	0	0
Rugosité Parker	ISO 8791-4	TAPPI T555	µm	±30%	1,8	1,8	0	0	0
Humidité relative	-	TAPPI T502	%	± 7	50	50	50	50	50

- Dernière actualisation : **27-10-17**
- Ces valeurs peuvent être modifiées sans avis préalable.

IT Carta Patinata Silk

Proprietà			Unità	Tolleranza					
Grammatura	ISO 536	TAPPI T410	gsm	± 4%	135	150	200	250	300
Spessore	ISO 534	TAPPI T411	µm	± 4%	115	131	166	220	265
Bianco R457 D65	ISO 2470-2	-	%	± 2	96	96	96	96	96
Bianco CIE D65/10°	ISO 11475	-	-	± 3	119	119	119	119	119
Opacità	ISO 2471	TAPPI T519	%	-2.0	96,0	97,0	0	0	0
Rugosità Parker	ISO 8791-4	TAPPI T555	µm	±30%	1,8	1,8	0	0	0
Umidità relativa	-	TAPPI T502	%	± 7	50	50	50	50	50

- Ultima revisione: **27-10-17**
- I valori sono soggetti a modifiche senza preavviso.

PT Couché 2 Faces Semi-mate

Propriedade			Unidade	Tolerância					
Gramagem	ISO 536	TAPPI T410	gsm	± 4%	135	150	200	250	300
Calibre	ISO 534	TAPPI T411	µm	± 4%	115	131	166	220	265
Brancura R457 D65	ISO 2470-2	-	%	± 2	96	96	96	96	96
Brancura CIE	ISO 11475	-	-	± 3	119	119	119	119	119
Opacidade	ISO 2471	TAPPI T519	%	-2.0	96,0	97,0	0	0	0
Aspereza Parker	ISO 8791-4	TAPPI T555	µm	±30%	1,8	1,8	0	0	0
Humidade relativa	-	TAPPI T502	%	± 7	50	50	50	50	50

- Última actualização: **27-10-17**
- Os valores estão sujeitos a mudanças sem pré-aviso.