



J. VILASEGA S. A.

FABRICA DE PAPEL DESDE 1.714

NATURAL

Material de crédito FSC certificado SGS-COC-2345

Specification	Unit	Norm	Value	Tolerances
Gramaje Substance Grammage	g/m^2	ISO 536	70, 80, 90, 100, 112, 120, 125, 140, 160, 200, 250, 300, 350	+/- 4 %
Espesor Caliper Épaisseur	μm	ISO 534	70 gr. 92 80 gr. 102 90 gr. 112 100 gr. 122 112 gr. 134 120 gr. 144 125 gr. 150 140 gr. 164 160 gr. 184 200 gr. 230 250 gr. 275 300 gr. 318 350 gr. 371	+/- 5 %
Porosidad Porosity Porosité	Índice	ISO 5636-5	10	+/- 5
Lisura Bekk Smoothness Bekk Lissé Bekk	s	ISO 5627	70 gr/m ² 30 > 71 gr/m ² 21	+/- 5
Humedad absoluta Absolute moisture Humidité absolute	%	ISO 287	< 160 g/m ² 5,5 > 161 gr/m ² 6,5	+/- 1
Blancura Brightness Blancheur	R457	ISO 2470	88	+/- 2
Encolado Water absorption Collage	COBB-60 g/m^2	ISO 535	22	+/- 3

Los datos citados son indicativos.

La estructura y los valores de la información de los productos pueden ser modificados.

Ref: 805/020/00/R10

Marzo 2023



J.VILASECA S. A.

FABRICA DE PAPEL DESDE 1.714

