

**TECHNICAL SPECIFICATION**

**OCTOBER 2022**

SUBSTANCE	CALIPER	BULK	STIFFNESS TABER 15° (*)		STIFFNESS L&W 5° (*)	
			MD	CD	MD	CD
ISO 536	ISO 534	ISO 534	ISO 2493		DIN 53121	
g/m <sup>2</sup>	µm	cm <sup>3</sup> /g	mNm	mNm	mNm	mNm
300	407	1.36	13.5	6.0	27.0	11.8
325	445	1.37	17.0	7.5	33.0	14.5
350	485	1.38	20.0	8.8	40.0	17.5
375	530	1.41	24.6	10.8	49.0	21.4
400	555	1.39	29.6	13.0	59.2	25.8
425	585	1.38	35.1	15.4	68.6	29.9
450	620	1.37	41.6	18.2	80.3	35.1
475	670	1.41	47.0	20.5	91.6	39.9

(\*) TABER VALUES ARE GUARANTEED. L&W FIGURES ARE CALCULATED.

BRIGHTNESS		
TOP	79.5%	ISO 2470-2

TOLERANCES - SAMPLING ISO 186 (*)		
SUBSTANCE	+/- 4%	
CALIPER	+/- 5%	
STIFFNESS	- 15%	
BRIGHTNESS	+/- 1.5	
TEST CONDITIONS	T: 23° C +/- 1	RH: 50% +/- 2

(\*) TOLERANCES BASED UPON 95% OF THE MEASURED VALUES.