

## Technical Data Sheet

### ZOOM 80GR

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m <sup>2</sup>	80
Thickness	ISO 534	µm	106
Bulk	ISO 534		1.33
Moisture Content	ISO 287	%	4.1
Roughness	ISO 8791	Bendtsen ml/min	220
Whiteness	ISO 11475	CIE	150
Brightness D65	ISO 2470-2	%	107
Opacity	ISO 2471	%	91

#### Production sites:

The production mills operate in compliance with the following standards



#### Special Attributes:



References:  
Product is made taking into account requirements of DIN EN 12281  
Product made from ECF Pulp  
ISO 45001 - Health & Safety  
ISO 50001 - Energy